



Hybrid Fabric

WOVEN FABRIC DATA SHEET

G. Angeloni reference

GK 210 T

CHARACTERISTICS	
Mass per unit area	gr/sqm.
Weave	
Standard Width	mm.
Laminate thickness	mm.
Other informations	

Nominal	Tolerance	Normative
213	± 5%	ISO 4605
2 x 2 Twill		ISO 2113
1000/1200	± 2,5%	
0,24	± 15%	ISO 5084
Loomstate		

Nominal Construction	
Fibre description	
Thread Count	ends/cm.
Weight Rate	%
Weight distribution	gr/sqm.
	%
	gr/sqm.
	%

WARP		WEFT	
3K Carbon fibre 200 tex		3K Carbon fibre 200 tex	
HM Aramid 1210 dtex		HM Aramid 1210 dtex	
6,30	ISO 4602	6,30	ISO 4602
50%		50%	
3K Carbon fibre	64	3K Carbon fibre	64
	61%		61%
HM Aramid	42	HM Aramid	42
	39%		39%

Note : Technical information furnished is based on laboratory findings and believed to be correct. No warranties of any kind are made except that the materials supplied are of standard quality. All risk and liabilities arising from handling, storage and use of products, as well as compliance with applicable legal restrictions, rests with the user.

G. Angeloni srl

via Abate Tommaso , 72/A5 - 30020 Quarto d'Altino (VE) - ITALY

Tel. +39 0422 823801 - 780580 Fax +39 0422 782782

E-Mail : info@g-angeloni.com