

### AZIENDA CON SISTEMA DI GESTIONE QUALITÀ CERTIFICATO DA DNV

= ISO 9001 =



#### **TECHNICAL DATA SHEET**

## M01C57

Mastic with fibreglass and catalysis indicator based on polyester resin, indicated for spatula application.

Suitable for assembling and filling of fibreglass parts and for preventing of defects in fibreglass products. The resin used give the product good adhesion and flexibility performance. Also the particular formulation allows to get limited cost.

#### **Chemical-physics characteristics**

PROPERTY	TYPICAL VALUE	UNIT	METHOD
ASPECT GEL TIME (at 25 °C)* DENSITY (at 25°C) STORAGE STABILITY**	blue adhesive 15 1.5 3	 minutes g/cm³ months	I.O.803 I.O.805

<sup>\*</sup> Adehsive 200 g. + 2% MEKP50.

**Application:** add 1-2% of mekp50 and apply by hand (with spatula).

The presence of catalysis indicator allow to check the homogeneity of the

iniziator dispersion.

The high thixotropy index allow the use of mastic also on vertical surfaces, with

high thickness, without leakage.

# Characteristics of cured product

PROPERTY	TYPICAL VALUE	UNIT	METHOD
BONDING RESISTANCE	5	N/mm²	ASTM D 3163-01

REV.1: 06/12/11

The information contained in this datasheet is based on laboratory data and our experience. Gel time and rheological properties may change because of reactive nature of material. We believe this information to be reliable, however we cannot guarantee its applicability in your process. We decline all responsibility for events that may arise as a consequence of improper use of the product.

By accepting the products described herein, the user accepts the responsibility to thoroughly test any application before commencing production.

Our advice should not be taken as encouragement to breach any patent, law, safety code or insurance regulation.

<sup>\*\*</sup> The adhesive must be stored in original containers, sealed and not damaged, in a dry place, at a temperature between 5°C and 25°C.